CLAIM AMENDMENTS:

1-18 cancelled

19. (new) A cotton swab for cosmetic or medical purposes or for body care, the swab comprising:

a stick; and

- a fiber material forming a cotton head at at least one end of the stick, the fiber material comprising micro staple fibers of at least 7mm in length.
- 20. (new) The cotton swab of claim 19, wherein the micro staple fibers are polyester (PES) or viscose fibers.
- 21. (new) The cotton swab of claim 19, wherein a portion of micro staple fibers compared to a mass of said fiber material is 3 to 50 weight %.
- 22. (new) The cotton swab of claim 21, wherein a portion of micro staple fibers compared to a mass of said fiber material is 5 to 30 weight %.
- 23. (new) The cotton swab of claim 22, wherein a portion of micro staple fibers compared to a mass of said fiber material is 5 to 20 weight %.
- 24. (new) The cotton swab of claim 19, wherein said fiber material additionally comprises up to 97 weight % of cotton fibers.

- 25. (new) The cotton swab of claim 24, wherein said fiber material additionally comprises up to 60 to 97 weight % of cotton fibers.
- 26. (new) The cotton swab of claim 25, wherein said fiber material additionally comprises up to 70 to 95 weight % of cotton fibers.
- 27. (new) The cotton swab of claim 24, wherein said cotton fibers are cotton noils.
- 28. (new) The cotton swab of claim 19, wherein said fiber material comprises thermally meltable binding fibers.
- 29. (new) The cotton swab of claim 28, wherein a portion of said thermally meltable binding fibers compared to a mass of said fiber material is 5 to 20 weight %.
- 30. (new) The cotton swab of claim 29, wherein a portion of said thermally meltable binding fibers compared to a mass of said fiber material is 5 to 15 weight %.
- 31. (new) The cotton swab of claim 28, wherein said thermally meltable binding fibers are multi-component fibers or bi-component fibers.
- 32. (new) The cotton swab of claim 31, wherein said multi-component fibers have a fiber thickness of 1.3 to 10 dtex.
- 33. (new) The cotton swab of claim 32, wherein said multi-component fibers have a fiber thickness of 1.3 to 3 dtex.
- 34. (new) The cotton swab of claim 31, wherein said multi-component fibers have a fiber length of 3 to 60 mm.

- 35. (new) The cotton swab of claim 28, wherein said binding fibers are copolyester (CO-PES) / polyester (PES) bi-component fibers.
- 36. (new) The cotton swab of claim 31, wherein a melting point of said thermally meltable binding fibers or of a low melting component of said multi-component fibers is lower than a melting point of said micro staple fibers.
- 37. (new) The cotton swab of claim 19, wherein a removal resistance of said fiber material from said end of said stick is larger than 30N.
- 38. (new) The cotton swab of claim 37, wherein a removal resistance of said fiber material from said end of said stick is larger than 40N.
- 39. (new) The cotton swab of claim 19, wherein a sinking duration of said fiber material in an aqueous solution is at least 3 seconds.
- 40. (new) The cotton swab of claim 39, wherein a sinking duration of said fiber material in an aqueous solution is at least 3.4 seconds.
- 41. (new) The cotton swab of claim 40, wherein a sinking duration of said fiber material in an aqueous solution is at least 4 seconds.
- 42. (new) The cotton swab of claim 40, wherein a sinking duration of said fiber material in an aqueous solution is at least 4.5 seconds.
- 43. (new) The cotton swab of claim 19, wherein a water retaining capacity of said fiber material is at least 21 g/g (g liquid per g fiber material).

- 44. (new) The cotton swab of claim 43, wherein a water retaining capacity of said fiber material is at least 23 g/g (g liquid per g fiber material).
- 45. (new) The cotton swab of claim 19, wherein said fiber material contains a softener.
- 46. (new) The cotton swab of claim 19, wherein said fiber material forming said cotton head is produced from a fiber fleece or a fiber fleece strip having a specific weight of 0.5 to 8 g/m.
- 47. (new) The cotton swab of claim 46, wherein said fiber material forming said cotton head is produced from a fiber fleece or a fiber fleece strip having a specific weight of 1 to 2 g/m.
- 47. (new) The cotton swab of claim 46, wherein said fiber fleece or the fiber fleece strip is a card fleece which is oriented in a machine direction.